

2TE

DIN EN 854 2TE



内胶层：耐油合成橡胶
 增强层：2层高抗拉纤维编
 织外层：耐天候合成橡胶
 主要应用：低压管，回油管

连续作业：-40 ~+100

最高工作温度：121

建议使用流体介质：矿物油、菜油和油菜
 籽油、二醇和聚乙二醇基油、合成酯基油
 、水/乳化油

HOSE SIZE		R.O.D		O.D		MAX W.P		RURST PRESSURE		MIN.BEND RADIUS		WEIGHT	
DN	inch	mm	inch	mm	inch	bar	psi	bar	psi	mm	inch	kg/m	lb/ft
6	1/4"			14.5	0.57	75	1080	300	4350	40	1.57	0.16	
8	5/16"			16.8	0.66	68	980	272	3940	50	1.97	0.19	
10	3/8"			18.6	0.73	63	910	252	3650	60	2.36	0.24	
12	1/2"			22.5	0.89	58	840	232	3360	70	2.76	0.32	
16	5/8"			26.2	1.03	50	720	200	2900	90	3.54	0.39	
19	3/4"			29.5	1.16	45	650	180	2610	110	4.33	0.52	
25	1"			36.0	1.42	40	580	160	2320	130	5.12	0.66	
31	1.1/4"			43.5	1.71	35	500	140	2030	140	5.51	1.05	
38	1.1/2"			63.8	2.50	27	390	108	1560	360	14.17	1.65	
51	2"			73.0	2.87	25	360	100	1440	500	19.69	1.93	